



GEL VALVE REGULATED RECHARGEABLE BATTERY



MODEL: G12-150(12V 150AH)

SOLAR BATTERY

LEGACY CANADIAN PRODUCTS
DESIGNED IN CANADA,
ASSEMBLED IN CHINA

 www.connectinglegacy.com

1.PRODUCT DIMENSIONS




G12-150(12V 150AH)

BATTERY DIMENSION (MM)	LENGTH	484
	WIDTH	171
	HEIGHT	241
	TOTAL HEIGHT	241
BOX DIMENSION (MM)	LENGTH	499
	WIDTH	185
	HEIGHT	299
QUANTITY PER BOX		1PC
N.W PER CELL (KG)±400g		43.0
N.W PER BOX (KG)		43.0
G.W PER BOX (KG)		44.0

2.PRODUCT CHARACTERISTICS

NOMINAL VOLTAGE		12V
NOMINAL CAPACITY (10 HOUR RATE)		150AH
CAPACITY @25°C (77°F)	20 HOUR RATE(13.6A)	165.0AH
	5 HOUR RATE(24.0A)	125.0AH
	1 HOUR RATE(88.3A)	88.3AH
CYCLE LIFE(@25°C)	100%DOD	800 TIMES
	50%DOD	1250 TIMES
	30%DOD	1750 TIMES
DESIGN LIFE		8 YEARS
SELF-DISCHARGE(@25°C)		< 3%/MONTH
INTERNAL RESISTANCE		FULL CHARGED BATTERY 25°C ≤3.5mΩ
CHARGE (CONSTANT VOLTAGE) @25°C(77°F)	FLOAT	INITIAL CHARGING CURRENT LESS THAN 30.0A VOLTAGE 13.6-13.8V
	CYCLE	INITIAL CHARGING CURRENT LESS THAN 30.0A VOLTAGE 14.4-14.9V

G12-150(12V 150AH)




TERMINAL:M8

3. DISCHARGE CONSTANT CURRENT PER CELL


F.V/TIME	5MIN	10MIN	15 MIN	30MIN	45MIN	1H	2H	3H	5H	8H	10H	20H
1.60V	380.0	236.4	196.0	138.4	99.3	88.3	54.6	37.4	25.4	16.8	15.0	8.2
1.65V	373.1	232.1	192.4	135.9	97.5	86.7	53.6	36.7	25.0	16.5	14.7	8.1
1.70V	366.2	227.8	188.8	133.3	95.7	85.1	52.6	36.0	24.5	16.1	14.4	7.9
1.75V	359.3	223.5	185.3	130.8	93.9	83.4	51.6	35.4	24.0	15.8	14.1	7.8
1.80V	345.4	214.9	178.2	125.8	90.3	80.2	49.6	34.0	23.1	15.2	13.6	7.5

F.V/TIME	5MIN	10MIN	15 MIN	30MIN	45MIN	1H	2H	3H	5H	8H	10H	20H
1.60V	731.5	455.0	377.3	266.4	191.2	169.9	105.1	72.0	49.0	32.3	28.8	15.8
1.65V	718.2	446.7	370.4	261.5	187.7	166.8	103.2	70.7	48.1	31.7	28.3	15.6
1.70V	704.9	438.5	363.5	256.7	184.3	163.7	101.3	69.4	47.2	31.1	27.8	15.3
1.75V	691.6	430.2	356.7	251.9	180.8	160.6	99.4	68.1	46.3	30.5	27.2	15.0
1.80V	665.0	413.6	343.0	242.2	173.8	154.5	95.6	65.5	44.5	29.3	26.2	14.4

COMPONENT	POSITIVE PLATE	NEGATIVE PLATE	CONTAINER	COVER	SATETY VALVE	TERMINAL	SEPERATOR	ELECTROLYTE
RAW MATERIAL	LEAD DIOXIDE	LEAD	ABS	ABS	SI-RUBBER	COPPER	FIBERGLASS	GEL



**Amperes at
(77°F/25°C)**




**Watts at
(77°F/25°C)**

**Battery
Construction**

4. PERFORMANCE CHARACTERISTICS


Cycle life vs. Depth of discharge (25°C)



**CYCLE LIFE: 100%DOD 800TIMES
(@25°C) 50%DOD 1250TIMES
30%DOD 1750TIMES**

Temperature effect on float life

Float charging voltage: 13.65 ± 0.01V (25°C)





WORKING LIFE: UP TO 8 YEARS

WARRANTY: 2 YEARS

Note:1)The above datas are average values, and can be obtained within 3 charge/ discharge cycles. These are not minimum values.
2)Cell and battery designs/specifications are subject to modification without notice.

5. CHARGE AND DISCHARGE CHARACTERISTICS




FLOAT TEMPERATURE COMPENSATION COEFFICIENT(25°C): $-2\text{mV}/\text{Cell C}$

EQUALIZATION TEMPERATURE COMPENSATION COEFFICIENT(25°C): $-5\text{mV}/\text{Cell C}$

*Note: 1) The above data are average values, and can be obtained within 3 charge/ discharge cycles. These are not minimum values.
2) Cell and battery designs/specifications are subject to modification without notice.*

6. TEMPERATURE EFFECTED CHARACTERISTICS


Temperature effect on battery self-discharge



SELF-DISCHARGE CAPACITY(25°C):

AFTER 3 MONTHS: 92%
AFTER 6 MONTHS: 84%
AFTER 12 MONTHS: 65%

Temperature effect on capacity



CAPACITY AFFECTED BY TEMPERATURE:
40°C : 102%
25°C : 100%
0°C : 85%
-15°C : 65%

Note:

- 1)The above datas are average values, and can be obtained within 3 charge/ discharge cycles. These are not minimum values.
- 2)Cell and battery designs/specifications are subject to modification without notice.



LEGACY CANADIAN PRODUCTS
DESIGNED IN CANADA,
ASSEMBLED IN CHINA

LET'S DEVELOP TRUST AND BUSINESS

 www.connectinglegacy.com