



GEL VALVE REGULATED RECHARGEABLE BATTERY



MODEL: G12-9(12V 9AH)

SOLAR BATTERY

LEGACY CANADIAN PRODUCTS
DESIGNED IN CANADA,
ASSEMBLED IN CHINA

www.connectinglegacy.com

1.PRODUCT DIMENSIONS




G12-9(12V 9AH)

BATTERY DIMENSION (MM)	LENGTH	151
	WIDTH	65
	HEIGHT	95
	TOTAL HEIGHT	101
BOX DIMENSION (MM)	LENGTH	364
	WIDTH	165
	HEIGHT	141
QUANTITY PER BOX		5 PCS
N.W PER CELL (KG)±100g		2.52
N.W PER BOX (KG)		11.75
G.W PER BOX (KG)		12.2

2.PRODUCT CHARACTERISTICS

NOMINAL VOLTAGE		12V
NOMINAL CAPACITY (10 HOUR RATE)		9AH
CAPACITY @25°C (77°F)	20 HOUR RATE(11.0A)	8.8AH
	5 HOUR RATE(35.4A)	8.0AH
	1 HOUR RATE(132A)	6.6AH
CYCLE LIFE(@25°C)	100%DOD	250 TIMES
	50%DOD	450 TIMES
	30%DOD	800 TIMES
DESIGN LIFE	3 YEARS	
SELF-DISCHARGE(@25°C)	< 3%/MONTH	
INTERNAL RESISTANCE	FULL CHARGED BATTERY 25°C ≤20mΩ	
CHARGE (CONSTANT VOLTAGE) @25°C(77°F)	FLOAT	INITIAL CHARGING CURRENT LESS THAN 2.55A VOLTAGE 13.6-13.8V
	CYCLE	INITIAL CHARGING CURRENT LESS THAN 2.55A VOLTAGE 14.4-15.0V

G12-9(12V 9AH)




TERMINAL: F1

3.DISCHARGE CONSTANT CURRENT PER CELL


F.V/TIME	5MIN	10MIN	15 MIN	30MIN	45MIN	1H	2H	3H	5H	8H	10H	20H
1.60V	28.05	18.70	14.07	9.35	6.55	5.61	3.51	2.40	1.60	1.08	0.89	0.47
1.65V	27.54	18.36	13.81	9.18	6.43	5.51	3.44	2.36	1.57	1.06	0.87	0.46
1.70V	27.03	18.02	13.56	9.01	6.31	5.41	3.38	2.32	1.54	1.04	0.86	0.45
1.75V	26.52	17.68	13.30	8.84	6.19	5.30	3.32	2.27	1.51	1.02	0.84	0.44
1.80V	25.50	17.00	12.79	8.50	5.95	5.10	3.19	2.18	1.46	0.98	0.81	0.43

F.V/TIME	5MIN	10MIN	15 MIN	30MIN	45MIN	1H	2H	3H	5H	8H	10H	20H
1.60V	54.00	36.00	27.09	18.00	12.60	10.80	6.75	4.63	3.08	2.07	1.71	0.90
1.65V	53.01	35.34	26.59	17.67	12.37	10.60	6.63	4.54	3.03	2.04	1.68	0.88
1.70V	52.03	34.69	26.10	17.34	12.14	10.41	6.50	4.46	2.97	2.00	1.65	0.87
1.75V	51.05	34.03	25.61	17.02	11.91	10.21	6.38	4.37	2.92	1.96	1.62	0.85
1.80V	49.09	32.73	24.62	16.36	11.45	9.82	6.14	4.21	2.80	1.88	1.56	0.82

COMPONENT	POSITIVE PLATE	NEGATIVE PLATE	CONTAINER	COVER	SATETY VALVE	TERMINAL	SEPERATOR	ELECTROLYTE
RAW MATERIAL	LEAD DIOXIDE	LEAD	ABS	ABS	SI- RUBBER	COPPER	FIBERGLASS	SULFURIC ACID



**Amperes at
(77°F/25°C)**




**Watts at
(77°F/25°C)**

**Battery
Construction**

4. PERFORMANCE CHARACTERISTICS


Cycle life vs. Depth of discharge (25°C)



CYCLE LIFE: 100%DOD 250TIMES
(@25°C) 50%DOD 450TIMES
30%DOD 800TIMES

Temperature effect on float life

Float charging voltage: 13.8 ±0.01V (25°C)





WORKING LIFE: UP TO 3 YEARS

WARRANTY: 1 YEAR

Note:1)The above datas are average values, and can be obtained within 3 charge/ discharge cycles. These are not minimum values.

2)Cell and battery designs/specifications are subject to modification without notice.

5. CHARGE AND DISCHARGE CHARACTERISTICS




FLOAT TEMPERATURE COMPENSATION COEFFICIENT($25^{\circ}C$): $-2mV/Cell\ C$

EQUALIZATION TEMPERATURE COMPENSATION COEFFICIENT($25^{\circ}C$): $-6mV/Cell\ C$

*Note:1)The above datas are average values, and can be obtained within 3 charge/ discharge cycles. These are not minimum values.
 2)Cell and battery designs/specifications are subject to modification without notice.*


6. TEMPERATURE EFFECTED CHARACTERISTICS

Temperature effect on battery self-discharge



SELF-DISCHARGE CAPACITY(25°C):
AFTER 3 MONTHS: 92%
AFTER 6 MONTHS: 82%
AFTER 12 MONTHS: 65%

Temperature effect on capacity



CAPACITY AFFECTED BY TEMPERATURE: (10 HOUR)
40°C : 102%
25°C : 100%
0°C : 85%
-15°C : 65%

Note:

- 1)The above datas are average values, and can be obtained within 3 charge/ discharge cycles. These are not minimum values.
- 2)Cell and battery designs/specifications are subject to modification without notice.



LEGACY CANADIAN PRODUCTS
DESIGNED IN CANADA,
ASSEMBLED IN CHINA

LET'S DEVELOP TRUST AND BUSINESS

🌐 www.connectinglegacy.com