

Model: GL12-100(12V 100Ah)

GL Series

VLRA High Rate Discharge Battery



Legacy Canadian products designed in Canada, assembled in China.





Introduction	GL12-100(12V 100Ah)		2EGACY
Length	328±2mm (12.9 inches)		
Width	172±2mm (6.77 inches)	328	172
Height	215±2mm (8.46 inches)		
Total Height	220±2mm (8.66 inches)		220
Weight	Approx. 28.5 Kg (Tolerance±5%)		
Terminal	Default F12(M8), F5(M8) and L7(Optional), Value: 10~12N*m		045
Container Material	A.B.S. UL94-HB, <ul94-v0 optional=""></ul94-v0>		M8
Design Life	12 years	3 - + -	
Application	UPS/EPS,Telecom,Power grid,Medical equiment,Emergency light and Security system etc.	265	
	Structure: Compact design of shorter internal connectors among cells for lower I.R.		F12 Terminal
	Plate: Pasted flat type with patent high rate formula of AM supports stable performance du discharge.	ring high current	GL12-100 Dimension
Features	Separator: Improved AGM seperator increases deep cycle life.		
	Safety Valve:Flame arrester/filter is equipped with safety valve system.		
	Design and manufacture with DIN standards by Legacy team, for heavy load discharge applic	cations.	1



Parameters	GL12-100 (12V 100Ah)	
Cell Per Unit	6	
Voltage Per Unit	12V	
Nominal Capacity	100Ah @10hour-rate to 1.80V per cell @25°C	
Internal Resistance	≤5.5 mΩ(Full Charge Condition @25°C)	
Max. Discharge Current	1000A (5 sec)	
Max. Charging Current	30.0A	LEG
Short Circuit Current	2150A	A A ®
Reference Capacity	C3:75.0Ah C5:85.0Ah C10: 100.0Ah C20: 106.0Ah	
Floating Charging Voltage	13.5 V~13.8 V @ 25°C Temperature Compensation: -3mV/°C/Cell	
Cycle Use Voltage	14.6 V~14.8 V @ 25°C Temperature Compensation: -4mV/°C/Cell	
Normal Operating Temperature Range	25°C±5°C	
Operating Temperature Range	Discharge and Storage : -20°C~60°C Charge: 0°C~50°C	
Self Discharge	Monthly Self-discharge ratio is less than 3% at 25°C	
Note	Legacy GL batteries can be stored for up to 6 months at 25°C and recharging is recommended. Please charged batteries before using.	

GL12-100 Imagine




F.V/TIME	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	231.9	185.4	109.5	`61.1	36.4	28.2	22.2	18.9	12.7	10.5	5.52
1.65V	219.1	177.3	105.1	59.0	35.2	27.3	21.6	18.4	12.5	10.4	5.43
1.70V	201.7	166.0	100.5	57.1	34.1	26.6	21.0	17.9	12.3	10.3	5.36
1.75V	184.6	154.5	96.0	55.0	32.9	25.8	20.4	17.4	12.2	10.1	5.30
1.80V	167.1	142.7	91.8	52.9	31.7	25.0	19.9	17.0	12.0	10.0	5.25
1.85V	136.6	118.4	79.1	47.4	29.1	23.1	18.5	15.9	11.2	9.41	4.98


Constant Current Discharge Ah/Cell (@ 77°F/25°C)

Model: GL12-100


F.V/TIME	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	394.1	324.1	198.9	114.8	69.0	53.9	42.6	36.4	24.8	20.7	10.9
1.65V	379.6	314.5	193.0	111.5	67.1	52.4	41.6	35.6	24.5	20.5	10.7
1.70V	355.9	298.9	186.3	108.6	65.3	51.2	40.6	34.8	24.2	20.2	10.6
1.75V	331.6	282.2	179.9	105.2	63.3	49.9	39.7	34.0	23.9	20.0	10.5
1.80V	305.4	264.3	173.7	101.8	61.3	48.6	38.7	33.2	23.6	19.8	10.4
1.85V	254.1	222.4	151.1	91.9	56.5	45.1	36.1	31.1	22.2	18.6	9.87



Discharge Characteristics Curve




Cycle Life in Relation to Depth of Discharge




Charge Characteristics Curve For Standby Use(IU)






Relationship Between Charging Voltage and Temperture




Note: The above datas are average values, and can be obtained within 3 charge / discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice. Legacy reserves the right to explain and update the lastest information.

Life Characteristics of Standby Use




Effect of Temperture on Longterm life



Storage Characteristics






Supplementary charge required (Carry out supplement charge before use if 100% capacity is required

Supplementary charge required before use. This supplementary charge will help to recover the capacity and should be made as early as possible

Supplementary charge may often fail to recover the capacity.
The battery should never be left standing till this state is reached.

Supplementary charge and storage guidelines

Temperautre Effects On Capacity



Note: The above datas are average values, and can be obtained within 3 charge/discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice. Legacy reserves the right to explain and update the lastest information.



LET'S DEVELOP TRUST AND BUSINESS

Connecting To Legacy