

Model: GL12-80(12V 80Ah)

GL Series

VLRA High Rate Discharge Battery



Legacy Canadian products designed in Canada, assembled in China.

Connecting To Legacy

Laval-Quebec-Canada

Beirut-Lebanon

Hongkong-China

www.connectinglegacy.com



Introduction	GL12-80(12V 80Ah)		,	ZEGZICI
Length	350±2mm (13.8 inches)			
Width	167±2mm (6.57 inches)	350		167
Height	182±2mm (7.17 inches)		-	
Total Height	182±2mm (7.17 inches)] 		175.5
Weight	Approx. 21.5 Kg (Tolerance±5%)			
Terminal	Default F11(M6), Value: 8~10N*m and F5(M8)(Optional), Value: 10~12N*m			Φ14 M6
Container Material	A.B.S. UL94-HB, <ul94-v0 optional=""></ul94-v0>			
Design Life	12 years			
Application	UPS/EPS,Telecom,Power grid,Medical equiment,Emergency light and Security system etc.	265		\Box
	Structure: Compact design of shorter internal connectors among cells for lower I.R.			F11 TERMINAL
	Plate: Pasted flat type with patent high rate formula of AM supports stable performance during high condischarge.	GL12-80	Dimension	
Features	Separator: Improved AGM seperator increases deep cycle life.			
	Safety Valve:Flame arrester/filter is equipped with safety valve system.			
	Design and manufacture with DIN standards by Legacy team, for heavy load discharge applications.			1




Parameters	GL12-80 (12V 80Ah)	
Cell Per Unit	6	
Voltage Per Unit	12V	
Nominal Capacity	80Ah @10hour-rate to 1.80V per cell @25°C	
Internal Resistance	≤6.0 mΩ(Full Charge Condition @25°C)	
Max. Discharge Current	800A (5 sec)	
Max. Charging Current	24.0A	LEG
Short Circuit Current	1840A	NA AND
Reference Capacity	C3:60.0Ah C5:68.0Ah C10: 80.0Ah C20: 84.8Ah	
Floating Charging Voltage	13.6 V~13.8 V @ 25°C Temperature Compensation: -3mV/°C/Cell	
Cycle Use Voltage	14.6 V~14.8 V @ 25°C Temperature Compensation: -4mV/°C/Cell	
Normal Operating Temperature Range	25°C±5°C	
Operating Temperature Range	Discharge and Storage : -20°C~60°C Charge: 0°C~50°C	
Self Discharge	Monthly Self-discharge ratio is less than 3% at 25°C	
Note	Legacy GL batteries can be stored for up to 6 months at 25°C and recharging is recommended. Please charged batteries before using.	

GL12-80 Imagine




F.V/TIME	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	195.3	148.3	87.6	48.9	29.1	22.6	17.7	15.1	10.1	8.44	4.41
1.65V	184.5	141.8	84.1	47.2	28.2	21.9	17.3	14.7	10.0	8.34	4.34
1.70V	169.9	132.8	80.4	45.7	27.3	21.3	16.8	14.3	9.87	8.21	4.29
1.75V	155.5	123.6	76.8	44.0	26.3	20.6	16.4	14.0	9.74	8.10	4.24
1.80V	140.7	114.1	73.4	42.3	25.4	20.0	15.9	13.6	9.57	8.00	4.20
1.85V	115.0	94.7	63.3	38.0	23.2	18.5	14.8	12.7	8.99	7.53	3.99


F.V/TIME	10MIN	15MIN	30MIN	1HR	2HR	3HR	4HR	5HR	8HR	10HR	20HR
1.60V	331.9	259.3	159.1	91.9	55.2	43.1	34.0	29.1	19.8	16.6	8.69
1.65V	319.7	251.6	154.4	89.2	53.7	41.9	33.2	28.4	19.6	16.4	8.57
1.70V	299.7	239.2	149.0	86.9	52.2	41.0	32.5	27.8	19.4	16.2	8.47
1.75V	279.3	225.8	143.9	84.2	50.6	39.9	31.8	27.2	19.1	16.0	8.38
1.80V	257.2	211.4	138.9	81.4	49.1	38.8	31.0	26.6	18.9	15.8	8.31
1.85V	213.9	177.9	120.8	73.5	45.2	36.1	28.9	24.9	17.7	14.9	7.90




Model: GL12-80



Discharge Characteristics Curve




Cycle Life in Relation to Depth of Discharge




Charge Characteristics Curve For Standby Use(IU)






Relationship Between Charging Voltage and Temperture




Note: The above datas are average values, and can be obtained within 3 charge / discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice. Legacy reserves the right to explain and update the lastest information.

Life Characteristics of Standby Use




Effect of Temperture on Longterm life



Storage Characteristics






Supplementary charge required (Carry out supplement charge before use if 100% capacity is required

Supplementary charge required before use. This supplementary charge will help to recover the capacity and should be made as early as possible

Supplementary charge may often fail to recover the capacity.
The battery should never be left standing till this state is reached.

Supplementary charge and storage guidelines

Temperautre Effects On Capacity



Note: The above datas are average values, and can be obtained within 3 charge/discharge cycles. These are not minimum values. Cell and battery designs/specifications are subject to modification without notice. Legacy reserves the right to explain and update the lastest information.



LET'S DEVELOP TRUST AND BUSINESS

Connecting To Legacy